

PRODUCT DATA SHEET
RUBBERALL® WHITE
COVER STRIP



Water Tight Technologies, LLC
P.O. Box 899, Payson, AZ 85547
www.watertighttech.com

Description: Rubberall® White Cover Strip is a laminate of cured white EPDM membrane and butyl tape rolled on a release paper to be used as a “self-sticking” cover strip for white EPDM or TPO roof membrane systems. The Cover Strip has been formulated to provide high green strength in both peel and shear. It is easily applied, offers significant labor savings and avoids the inherent solvent hazards of contact adhesives.

Suggested Uses: Rubberall® White Cover Strip should be used as a cover for metal drip edge, patching membrane or repairing seams or flashings.

Sizes: RUBBERALL® White Cover Strip has a nominal thickness of 0.075” +/- .005”
Rolls sizes available: 6” x 25’; 6” x 50’; 6” x 100’; 9” x 100’; 12” x 100’

General: This product usually has increased adhesion values when aged. Elevated temperatures usually encountered in single ply roof installations will cause the product to cure tighter; therefore, developing the increased test values. Due to the cross-linking that occurs during extrusion and thereafter; the product has excellent elevated temperature resistance.

Product Benefits:

- Labor Savings
- Cured Product - 12 month shelf life
- Superior performance over full range of environmental conditions
- Quick tack from high to low temperatures

Physical Properties

Property Type	Test Method	Specification	Test Results
Shear strength	ASTM D 816	23 PSI min. (1)	≥ Specification
Peel Strength	ASTM D 413	8 PLI min. (1)	≥ Specification
Tensile Strength	ASTM D 412	45 PSI min.	≥ Specification
Elongation	ASTM D 412	1000 % minimum	≥ Specification
Penetration	ASTM D 217	90 - 110 MM (3)	≥ Specification
Flash Point	ASTM D 92	350° F min.	≥ Specification
Low Temperature	ASTM D 746	Minus 50° F flexibility	≥ Specification

- (1) Testing done with primer applied to both sides of white EPDM or TPO membrane; cleaned with Membrane Cleaner. Samples aged for 24 hours @ 70° C prior to testing. Instron speed 2” min.
(2) Specimen cut with an ASTM die C or died. Sample pulled at 10”/ min and aged at 70° C for 72 hours.
(3) 300 gram cone load used.

Application Instructions:

1. The entire surface where the Cover Strip will be applied must be clean. The adhesive on the back will not adhere to dusty and or dirty surfaces. Remove dirt and excess dust from the surface area by wiping with a clean rag and if necessary, clean the area thoroughly with Membrane Cleaner.
2. Apply RUBBERALL® Tape Primer using RUBBERALL® Scrub Pads. Scrub the area of the membrane to be flashed or mated in a circular motion to achieve a thin even coating. The properly primed area will be uniform in color without streaks and free of globs of puddles.
3. The entire surface where the Cover Strip will be applied must be cleaned and primed. Always apply the primer to an area that is wider & longer than the Cover Strip. Any residual surface contamination will be detrimental to the bond strength of the adhesive.
4. Allow the Seam Tape Primer to dry until it does not transfer to a dry finger touch.
5. Remove backing and install Cover Strip immediately after the primer flashes off to minimize potential dust contamination and promote adhesion in colder weather.
6. Unroll and apply Cover Strip by pressing tape down to bottom surface using firm even hand pressure. Continue for the length of the area covered.
7. Rolling the Cover Strip with a steel hand roller after application to the primed substrate will significantly reduce the frequency of air blisters and assure adhesion.

Handling: RUBBERALL® Tape Primer contains ingredients that could be harmful if mishandled. Contact with eyes and skin should be avoided and protective equipment and clothing should be worn. Avoid prolonged skin contact.

Recommended Storage: RUBBERALL® White Cover Strip is a cured material and will not degrade in normal warehouse storage. Store in original unopened containers indoors at temperatures between 60° F and 80° F. Do not store in direct sunlight or at temperatures above 90° F for any extended period. In time, the release paper may become difficult to remove. For this reason, the recommended shelf life is 12 months. ROTATE STOCK.

NOTE: TECHNICAL INFORMATION AND DATA SHOULD BE CONSIDERED REPRESENTATIVE OR TYPICAL ONLY AND SHOULD NOT BE USED FOR SPECIFICATION PURPOSES.

User's Responsibility

This Product Data Sheet cannot cover all possible situations which the user may experience during product application/processing. Each aspect of your operations should be examined to determine if, or where, additional precautions may be necessary. All health and safety information contained in this bulletin should be provided to your employees or customers, along with the applicable MSDS sheet. It is your responsibility to use this information to develop appropriate work practice guidelines and employee instructional programs for your operation.

Disclaimer of Liability

As the conditions or methods of use are beyond our control, we do not assume any responsibility and expressly disclaim any liability for any use of this material. Information contained herein is believed to be true and accurate but all statements or suggestions are made without warranty, express or implied, regarding the accuracy of the information, the hazards connected with the use of the material or the results to be obtained from the use thereof. Compliance with all applicable federal, state and local laws and regulations remains the responsibility of the user.